

DESCRIPTION Deery[®] Packaged Asphalt 64-22 is asphalt complying with ASTM D6373 PG 64-22 packaged in CrafcO box packaging. DEERY Packaged Asphalt 64-22 VOC=0 g/l.

SPECIFICATION CONFORMANCE DEERY Packaged Asphalt 64-22, when tested according to ASTM D6373 for PG 64-22, Conforms to the following specification.

<u>PHYSICAL PROPERTIES</u>	<u>TEST METHOD (ASTM D6373)</u>	<u>SPECIFICATION</u>
ORIGINAL BINDER SPECIFICATIONS		
Flash Point, °C	ASTM D92	230°C min
Viscosity at 135°C, Pa.s	ASTM D4402	3.0 Pa.s max
Dynamic Shear, 10 rad/sec G*/sinδ at 64°C	ASTM D7175	1.00 kPa min
ROLLING THIN FILM OVEN RESIDUE (ASTM D2872)		
Mass Loss,	ASTM D2872	1.00% max
Dynamic Shear, 10 rad/sec G*/sinδ at 64°C	ASTM D7175	2.20 kPa min
PRESSURE AGING VESSEL RESIDUE AT 100°C (ASTM D652)		
Dynamic Shear, 10 rad/sec G*/sinδ at 64°C	ASTM D7175	5000 kPa min
Creep Stiffness, 60 sec.	ASTM D6648	
S at -12oC		300MPa max
m-value		0.300min

PACKAGING Product is supplied in cardboard boxes. Packages are labeled in accordance with OSHA, GHS, and specification requirements; are sold by net weight; are interlock stacked on 48 x 40 in. (122 x102 cm) 4-way pallets; can be stored outside; and are covered with a weather resistant pallet cover and 2 layers of UV protected stretch wrap. **BOX** packaging consists of cardboard boxes containing approximately 30 lb. (13.6 kg) of product with 75 boxes per pallet, weighing approximately 2250 lb. (1020 kg). Boxes contain a quick melting release film for easy removal and are taped closed, without any staples.

FOR ADDITIONAL INFORMATION
Call: 1-800-227-4059 Toll-Free
Email: info@deeryamerican.com
Visit: www.deeryamerican.com

PERFORMANCE Temperature fluctuations, site conditions, surface preparation, traffic, installation technique, material selection, shape factor and surface treatment compatibility influence the effectiveness and useful life of Pavement Preservation treatments. Consider and monitor each element for optimum results. Purchaser and end user should determine applicability for use in their specific conditions.

WARRANTY Manufacturer warrants that these products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, manufacturer shall not be responsible for improperly applied or misused products. Remedies against manufacturer, as agreed to by manufacturer, are limited to replacing nonconforming product or refund (full or partial) of purchase price from manufacturer. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by manufacturer, whichever is earlier. There shall be no other warranties expressed or implied. For optimum performance, follow manufacturer recommendations for product installation.