

DESCRIPTION DEERY SUPER GRAY is a light colored, hot applied, single component, elastically modified composition of non-asphaltic ingredients and modifiers. The sealant contains no solvent, is pre-reacted and when properly heated and applied, results in exceptional adhesion to both concrete and asphalt pavements. **Designed for use in recessed reservoir applications.** VOC=0 g/l.

USE DEERY SUPER GRAY is a moderate viscosity pavement preservation sealant intended for highway, street, aviation and parking area applications for recessed sealing of longitudinal and transverse joints and random cracks in Asphalt or Concrete pavements where a non-asphaltic, light colored material is desirable. Properly installed, DEERY SUPER GRAY is an effective barrier against damage from debris and moisture infiltration into cracks and joints within regions experiencing moderate high and low pavement temperatures.

HEATING Sealant shall be heated in a hot-oil jacketed or approved direct fire melter capable of constant mechanical agitation and equipped with a calibrated thermometer to monitor sealant temperature. Material shall be heated to and maintained at the Recommended Application Temperature during use. Material can be cooled and then reheated, but only if prolonged heating is avoided. Prolonged heating at or above Recommended Application Temperature may severely damage product. If overheating damage occurs, immediately drain machine completely and refill with new material.

APPLICATION DEERY SUPER GRAY is pre-reacted and can be applied immediately after heating to Recommended Application Temperature. With pavement temperature at 40°F (4°C) or higher, place material into clean, dry crack or prepared reservoir by means of a hand-held pour pot, wheeled applicator or wand applicator. To preserve color integrity, only fill to within 4 mm of surface. Squeegee any excess sealant tight to pavement surface and blot with limestone dust. Pavement may be warmed to 40°F (4°C) or higher with a Hot Air Lance.

PROPERTIES of DEERY SUPER GRAY

When sampled and heated to maximum heating temperature in accordance with ASTM D5167

<u>TEST</u>	<u>METHOD</u>	<u>SPECIFICATION</u>
Cone Penetration @ 77°F (25°C)	ASTM D5329	75 dmm maximum
Cone Penetration @ 122°F (50°C)	ASTM D5329	120 dmm maximum
Flow @ 140°F (60°C)	ASTM D5329	5.0 mm maximum
Resilience @ 77°F (25°C)	ASTM D5329	60% minimum
Flexibility, 90° bend, ¼" rod. 2 seconds	ASTM D3111 modified	Pass @ 20°F (-7°C)
Recommended Application Temperature	ASTM D5167	380-400°F (193-204°C)*
Maximum Heating Temperature	ASTM D6690	400°F (204°C)

*Temperature of product measured at pavement surface. Use highest Recommended Application Temperature in cool weather.
 *Prolonged heating at or above Recommended Application Temperature may severely damage product.

PACKAGING Material is packaged in cardboard boxes sized to accommodate a maximum of 40 lb (18.0 kg). Material contained in each box is wrapped in a quick melt liner which is dissolved and incorporated into the melted product. Standard packaging is 30 lb (13.6 kg) per box, palletized 75 boxes per pallet with an approximate net weight of 2,250 lb (1,021.0 kg). Pallets are moisture protected with a plastic wrapping and bound with a minimum of two layers of UV resistant stretch wrap.

FOR ADDITIONAL INFORMATION

Call: 1-800-227-4059 toll free
 Email: info@deeryamerican.com
 Web: www.deeryamerican.com

PERFORMANCE Temperature fluctuations, site conditions, surface preparation, traffic, installation technique, material selection, shape factor and surface treatment compatibility influence the effectiveness and useful life of Pavement Preservation treatments. Consider and monitor each element for optimum results. Purchaser and end user should determine applicability for use in their specific conditions.

WARRANTY Manufacturer warrants that these products meet applicable ASTM, AASHTO, Federal or State specifications at time of shipment. Techniques used for the preparation of the cracks and joints prior to sealing or filling are beyond our control as are the use and application of the products; therefore, manufacturer shall not be responsible for improperly applied or misused products. Remedies against manufacturer, as agreed to by manufacturer, are limited to replacing nonconforming product or refund (full or partial) of purchase price from manufacturer. All claims for breach of this warranty must be made within three (3) months of the date of use or twelve (12) months from the date of delivery by manufacturer, whichever is earlier. There shall be no other warranties expressed or implied. **For optimum performance, follow manufacturer recommendations for product installation.**

