

6165 W Detroit St. • Chandler AZ 85226
+1 (602) 276-0406 • +1 (800) 528-8242 • FAX +1 (480) 961-0513
www.deeryamerican.com

Product shall be supplied in 30 lb. (13.6 kg) completely meltable packages that are interlock stacked on pallets containing 2100 lb. (952 kg) of product. The individual packages and palletized unit shall not contain any cardboard components to open, empty, handle, or dispose of. Packages shall be labeled in accordance with OSHA, GHS and ASTM requirements. The packages and palletized unit shall be water and weather resistant and shall be able to be stored outside.

The individual packages of product shall be encased in a high-strength, low-density, protective covering that quickly melts into the product at normal use temperatures without affecting product installation characteristics or specification conformance.

The protective covering shall not weigh more than 0.50% of the product weight and shall have the following properties:

Thickness (ASTM D1777, 7.15 psi, 0.625 in. dia. presser)	0.004-0.008 in. (0.10-0.20 mm)
Puncture Resistance (ASTM E 154)	75 lb. (334N) minimum
Tensile Strength (ASTM D5035, cut strip, 2 in. /min)	20 lb. /in. (35N/cm) minimum
Density (ASTM D792)	0.50 g/cc maximum